



artisticgrafica.it

dynamic

by



CERAMICHE ASCOT S.R.L.
VIA CROCE, 80 - 41014 SOLIGNANO (MO) - ITALY
TEL. +39 059 77.84.11 - FAX +39 059 77.84.44/43
info@ascot.it - www.ascot.it

LE FORNACI

33,3x33,3 - 13"x13"

dynamic





FN050S Le Fornaci Rosato 33,3x33,3 13"x13" **548**




FN020S Le Fornaci Beige 33,3x33,3 13"x13" **548**




FN060S Le Fornaci Rosso 33,3x33,3 13"x13" **548**




FNS0 Sestina Fornaci Rosato 11x33,3 4"x13" **512**




FNAS0 Ang. Sestina Fornaci Rosato 11x11 4"x4" **512**




FNS20 Sestina Fornaci Beige 11x33,3 4"x13" **512**



FNAS20 Ang. Sestina Fornaci Beige 11x11 4"x4" **512**




FNS60 Sestina Fornaci Rosso 11x33,3 4"x13" **512**



FNAS60 Ang. Sestina Fornaci Rosso 11x11 4"x4" **512**




FN100 Listello Fornaci 11x33,3 4"x13" **518**




FNAL00 Angolo Fornaci 11x11 4"x4" **512**

dynamic 










FNB20 Battiscopa Beige 8x33,3 3"x13" **505**
FNB50 Battiscopa Rosato 8x33,3 3"x13" **505**
FNB60 Battiscopa Rosso 8x33,3 3"x13" **505**



FNTG20 Toro Gradino Beige 5x33,3 2"x13" **535**
FNTG50 Toro Gradino Rosato 5x33,3 2"x13" **535**
FNTG60 Toro Gradino Rosa 5x33,3 2"x13" **535**

Deti tecnici secondo norme:
Tecnical data conform to:
Caractéristiques techniques d'après normes:
Technische Daten nach den Normen:

EN14411-2:2003
Appendice: G
Gruppo BT₁ GL

Caratteristiche tecniche Technical data Caractéristiques techniques Technische Daten	Norme Normes Norm	Valori esecuti Value escot Valeur escot Wert escot
 Resistenza all'abrasione Abrasion resistance Résistance à l'abrasion Abrasionswiderstandigkeit	ISO 10545-7	PEI IV
 Assorbimento d'acqua Water absorption Absorption d'eau Wasser Aufnahme	ISO 10545-3	≤ 0,1%
 Resistenza alla flessione Breaking modulus Résistance à la flexion Biegefestigkeit	ISO 10545-4	40 - 55 N/mm ²
 Durezza Mohs Mohs hardness Dureté Mohs Härte Mohs	UNI 101	IV
 Resistenza all'attacco acido e basico Glaze resistance to acid and alkali attack Résistance aux acides et aux bases Säure- und laugenfestigkeit	ISO 10545-13	Resiste Resists Resiste Beständig
 Resistenza al gelo Resistance to frost Résistance au gel Frostbeständigkeit	ISO 10545-12	Non gelive Frost proof Ingliff Frostsicher
 Scivolosità Slipperiness Degré de glissement Rutschhemmung	DIN 51130	R9

IMBALLI - PACKING - VERPACKUNG - EMBALLAGE - EMBALAJE

FORMATO	MQ./SCATOLA	PEZZI/SCATOLA	KG./SCATOLA	SCATOLE/PALLET	MQ./PALLET	KG./PALLET
SIZE	SQM./BOX	PIECES/BOX	KG./BOX	BOXES/PALLET	SQM./PALLET	KG./PALLET
FORMAT	QM./KARTON	STÜCK/KARTON	KG./KARTON	KARTONS/PALETTE	QM./PALETTE	KG./PALETTE
FORMAT	M ² /BOITE	PIECES/BOITE	KG./BOITE	BOITE/PALETTE	M ² /PALETTE	KG./PALETTE
FORMATO	MQ./CAJA	PIEZAS/CAJA	KG./CAJA	CAJA/PALLET	MQ./PALLET	KG./PALLET
33,3x33,3 fondo	1770	16	29,00	42	74,34	1233
11x33,3 sestina	-	6	-	-	-	-
11x33,3 listello	-	6	-	-	-	-
11x11 ang. sestina	-	4	-	-	-	-
11x11 angolo	-	4	-	-	-	-
8x33,3 battiscopa	-	21	-	-	-	-
5x33,3 toro gradino	-	2	-	-	-	-